

Alkaline Battery Zn-MnO₂

Primary characteristics			
Parameter	Value	Unit	
Nominal voltage	1.5	V	
Rated capacity	1300	mAh	


Scope

The purpose of this product specification is to provide technical information for the alkaline Zn-MnO₂ battery AAA LRO3.

The test shall be conducted in strict accordance with the method specified in this specification.

If you have any objection to the test items or test methods, please contact Akyga Battery.





Specification table				
Parameter		Value	Unit	
Battery model		AAA LR03		
Nominal voltage		1.5	V	
Nominal capacity		1300	mAh	
Electrochemical system		Zinc Powder, KOH, Electrolyte Manganese Dioxide No added mercury, cadmium and lead		
Operating temperature		-20/+60	°C	
Average weight		23	g	

Notes:

Nominal capacity test conditions: 10mA resistive load, 24h/d, end voltage: 0.8V, operating temperature $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$ Shelf Life: 10 years (Temperature $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$, relative humidity $55\pm20\%$)

Electrical Performance:

Testing Conditions: Temperature: $20^{\circ}\text{C} \pm 2^{\circ}\text{C}$

Load resistance (±0.5%) 3.9 Ω Testing time: 0.3 seconds

	OVC [V]	Load voltage [V]	Accepted Levels
New battery (within 30 days of delivery)	≥1.58	≥1.40	MIL STD1055 II AOL-0 4
Storage after 12 months under the normal temperature	≥1.56	≥1.35	MIL-STD105E, II, AQL=0.4

Identification

The contents printed on the label:

Model: AAA LR03

Registered Trademark: Akyga Battery

Nominal Voltage: 1.5V Battery Poloidal: "+" and "-"


Warning words: Install and use correctly. Do not recharge, disassemble, heat and shot-circuit



Dischar	Discharge Performance						
	Discha	Discharge conditions		New	Minimum Average Duration		
	Load	Daily period	End voltage	battery discharge levels	New battery	With 20°C±2°C storage after 12 months	Applications
IEC IETMS	5.1Ω	4m/h 8h/d	0.9V	260min	250min	240min	torch
	5.1Ω	1h/d	0.8V	4.6h	4.4h	4.2h	toy
	24Ω	15s/m 8h/d	1.0V	21.0h	20.0h	19.0h	remote control
	50mA	1h/12h 24h/d	0.9V	22.0h	21.0h	20.0h	Digital Audio
	3.9Ω	24h/d	0.9V	165min	150min	135min	Discharge test

Testing Conditions: Temperature: 20°C ±2°C

Relative Humidity: RH55+20/-40% RH



Akyga battery Page 2/3 2024-04; REV. 1



Important notes

Keep away from source of fire and/or heat.

Do not recharge the alkaline batteries. May leak or explode if charged.

Do not disassemble battery and/or battery pack.

Remove batteries from device when it is not in use. Over discharge may destroy the appliance

Do not connect the positive and negative pole directly using conductive metal; avoid short circuit.

Do not put the battery into water or damp it.

Do not cut the battery.

Do not strike or needle the battery.

Charge the battery using specified chargers.

Do not solder the battery directly.

Observe the correct polarity (+/-).

Do not use the battery in un-specified application.

Do not mix the battery in usage with other types of battery.

Read the instruction manual carefully before use.

Akyga Battery reserves the right to make changes without notice to any product specification herein, to make corrections, modifications, enhancements or other changes. Akyga Battery or anyone on its behalf assumes no responsibility or liability for any errors or inaccuracies. Data sheet specifications and its information contained are intended to provide a product description only. "Typical" parameters which may be included on Akyga Battery data sheets and/ or specifications can and do vary in different applications and actual performance may vary over time. Akyga Battery does not assume any liability arising out of the application or use of any product or circuit. Akyga Battery products are not designed, intended or authorized for use in medical, life-saving implant or other applications intended for life-sustaining or other related applications where a failure or malfunction of component or circuitry may directly or indirectly cause injury or threaten a life without expressed written approval of Akyga Battery. Customers using or selling Akyga Battery components for use in such applications do so at their own risk and shall agree to fully indemnify Akyga Battery and its subsidiaries harmless against all claims, damages and expenditures.